



#### **Solder Reflow Recommendations**



Profile Feature	Pb-Free Assembly
Preheat / Soak:	
Temperature Min. (T <sub>smin</sub> )	150 °C
Temperature Max. (T <sub>smax</sub> )	200 °C
Time (t <sub>s</sub> ) from (T <sub>smin</sub> to T <sub>smax</sub> )	60~120 seconds
Ramp Up Rate (T <sub>L</sub> to T <sub>p</sub> )	3 °C / second max.
Liquidous Temperature (T <sub>L</sub> )	217 °C
Time (t <sub>L</sub> ) maintained above T <sub>L</sub>	60~150 seconds
Peak Package Body Temperature (T <sub>D</sub> )	260 °C
· ·	
Time (t <sub>p</sub> )* within 5 °C of the specified classification temperature (T <sub>c</sub> )	30 seconds*
Ramp Down Rate (T <sub>p</sub> to T <sub>L</sub> )	6 °C / second max.
Time 25 °C to Peak Temperature	8 minutes max.

<sup>\*</sup> Tolerance for peak profile temperature (Tp ) is defined as a supplier minimum and a user maximum.


## **Recommended Temperature Profile for Wave Soldering**




Wave soldering is suitable for 1210 size models.

# BOURNS

### **Current Rating Thermal Derating Curve**



### **Average Pre-Arcing Time vs. Current Curves**



### Average I2t vs. t Curves

