



## **Solder Reflow Recommendations**



| Profile Feature   | Pb-Free Assembly   |
|---|--------------------|
| Preheat / Soak:   |                    |
| Temperature Min. (T <sub>smin</sub> )   | 150 °C             |
| Temperature Max. (T <sub>smax</sub> )   | 200 °C             |
| Time (t <sub>s</sub> ) from (T <sub>smin</sub> to T <sub>smax</sub> )                             | 60~120 seconds     |
| Ramp Up Rate (T <sub>L</sub> to T <sub>p</sub> )  | 3 °C / second max. |
| Liquidous Temperature (T <sub>L</sub> )   | 217 °C             |
| Time (t <sub>L</sub> ) maintained above T <sub>L</sub>  | 60~150 seconds     |
| Peak Package Body<br>Temperature (T <sub>D</sub> )  | 260 °C             |
| Time (t <sub>p</sub> )* within 5 °C of the specified classification temperature (T <sub>C</sub> ) | 30 seconds*        |
| Ramp Down Rate (T <sub>p</sub> to T <sub>L</sub> )  | 6 °C / second max. |
| Time 25 °C to Peak Temperature  | 8 minutes max.     |

<sup>\*</sup> Tolerance for peak profile temperature (Tp ) is defined as a supplier minimum and a user maximum.

## **Recommended Temperature Profile for Wave Soldering**



Wave soldering is suitable for 1206 size models.



